

Technical Data Sheet

MENOS Natural Undercoat No. 626

PDF	MENOS Natural Undercoat No. 626
Application range	For interior wooden surfaces. Also suitable for fiberglass wallpaper surfaces.
Technical qualities	Flexible, matt.
Full declaration	Chalk, titanium dioxide, isoaliphates, linseed-stand-oil natural resin ester, mica, talc, orange oil, drying agents free of lead (Ca, Co, Zr), silicic acid, bentonite, citron oil, dehydrated amino sugar and ethanol.
Colors	White.
Dilution	With SVALOS Thinner No. 222, for spraying SVALOS Dipping and Spray Thinner No.293.
Application method	Apply sparingly using a brush, roller (undiluted) or spray device (maximum 10 % dilution) at temperatures above 150C (590F) and low humidity. Provide good light and airing conditions while drying.
Coverage	One undiluted liter is sufficient for 10-15 m ² (107-154 ft ²) per coat. Could be considerably less depending on the absorbency and the surface condition of the wood. Test application! Each dried coating may not exceed 50µm.
Cleaning	Clean equipment immediately after use With SVALOS Thinner No.222 or LEVO Brush Cleaner No.997.
Drying time	At 23 °C (73°F) and 50 % relative humidity, dry to the touch after approximately 3 hours. Sanding and subsequent coating may be done after 24. The paint is fully hardened after 6 - 7 days. Drying delays can be caused by to heavy coating, low temperatures or high humidity.
Specific gravity	Aprr. 1.45 g/ml.
Safety advice	Provide enough ventilation after application. Always be sure to store and then dispose of cleaning cloths, polishing pads, sponges, etc. that are still wet or even slightly moist with MENOS Natural Undercoat No. 626 in an airtight metal container or in water, as there is a danger of spontaneous combustion caused by the plant oil content. The product itself will not combust spontaneously. Contains limonene and cobalt (2+) salts. Can cause allergic reactions. S2 Keep out of reach of children. S62 If swallowed, do not induce vomiting. Seek medical assistance immediately, and show label or data sheet information.
Disposal	According to locally regulated laws.
Container sizes	0,375lt; 0,75lt; 2,5lt; 5lt.
Storage	Cool and dry. Shelf life: unopened at least 2 years. Close opened product tightly.

Important tips

MENOS Natural Undercoat No. 626

Preparation Surface must be dry (wood moisture content under 15%), solid, clean, and free of grease, resin and dust.

Application Stir thoroughly before use. Apply a sparing base coat of MENOS Natural Undercoat No. 626 with a brush, roller or spraying device at temperatures above 150C (590F). Do surface covering fine spackling with ANAVO Grain Filler No. 628 if necessary. Subsequent treatment with CANTO Natural White Satin Paint No.625, or CANTO Low Gloss Paint No. 690 (silky gloss) or VINDO Natural Gloss Paint No. 629 (high gloss).

Renovation Non-intact old coatings must be completely removed. Follow preparation and application instructions for untreated surfaces as above. Sand intact old coatings well, after testing compatibility, paint with 5 -10 % diluted CANTO Natural White Satin Paint No. 625 or VINDO Natural Gloss Paint No. 629.

Important tips

MENOS Natural Undercoat No. 626 should be applied sparingly. Spray applications must also be allowed to dry thoroughly. Too thickly applied coatings can impair drying properties and will cause cracking of subsequent paint coats.

MENOS Natural Undercoat No. 626 contains few solvents; this may cause a skin to build up. Please, remove before stirring. Transfer unused portions into smaller containers for storage. No liability is assumed for possible impaired adhesion as well as the development of odors resulting when MENOS No. 626 is painted over by products of other manufacturers. Do not paint over silicone.

Applying MENOS Natural Undercoat No. 626 mixed with 5 % by volume of quartz sand to plaster, will prevent impurities such as nicotine or water spots from surfacing. Subsequent coating with DUBRON Natural Dispersion Paint No. 400.

These directions are the result of long years of research and practical testing. They are backed by our most current expert information. New findings may invalidate this information. This data sheet is meant to serve as information and instruction. No legal liability should be interpreted from it. In case of doubt, please contact the retailer, wholesaler, or manufacturer.

Last updated 10-06-2009 14:30

[Back](#)