

- Preparation** Wood must be dry (wood moisture content max. 12 %), solid, absorbent and free of resin and dust. Sand gradually (identical for borders/room perimeters as the surface) according to the graduation of the sandpaper and up to 120 grain (for Australian timbers). For an even deepening of the natural color of the wood, sand up to 180 grain (for European timbers only).
- Manual application** Apply the first coat thinly with a spatula and polish in after max. 5 - 10 min. with a single disc rotary machine such as a Canterbury or Polyvac and a felt pad. For highly absorbent wood, and if an intensity or deepening of the natural color of the wood is wanted, the 2nd coat can be applied at the earliest after 48 hours.
- Industrial application** Mechanical application with solvent- and oil- resistant PU rollers at temperatures above 17 °C. After a drying time of at least 5 – 24 hours reevaluate the surface by polishing.
- Final coat** By economical dosage (max. 1 tsp/m²). For this, distribute the oil (e.g. KUNOS Natural Oil Sealer No. 244) drop by drop on the first or the second coat, spread it and polish in immediately and evenly with a single disc rotary machine and a felt pad.
- Care and maintenance** Do not wash in the first weeks, use only dry methods of cleaning
Clean with a damp, but not wet mop or cloth using TRENA pH-Neutral Cleaner No. 556 diluted in water. Maintenance should be carried out with KUNOS Floor Maintenance No. 1862 or KUNOS Natural Oil Sealer No. 244, when the surface looks matt.
- Important tips** Wood that is not completely saturated with KOIMOS High Solid Floor Oil No. 208 and then exposed to water may develop stains or discoloration.
Clean the roller coater before the oil film has dried.

These directions are the result of long years of research and practical testing. They are backed by our most current expert information. New findings may invalidate this information. This data sheet is meant to serve as information and instruction. No legal liability should be interpreted from it. In case of doubt, please contact the retailer, wholesaler, or manufacturer.

February 2011 Rev. 4.3